

**Release Liner**

Matt PET, siliconized on one side, 75 µm

**Adhesive**

Solvent polyacrylate, transparent, permanent

**Technical Data**

<b>Total Thickness</b>	190 micron
<b>Dimensional stability</b>	Adhered to steel, shrinkage 0,2 mm max.
<b>Resistance to solvents and chemicals</b> Immerse for 1 hour at RT (water), 30 Min at 45°C (acid, Pancreatin, tree gum), 10 Min (Gasoline E10), Check after 24 hours at RT	Water Sulfuric Acid (10%) Hydrochloric Acid (10%) Bird droppings (Pancreatin)      No Detrimental Effect Tree gum Gasoline E10
<b>Gloss</b>	>90 (GU)
<b>Adhesive Power</b> (180°, after 24h stainless steel)	≥17 N/25 mm
<b>Tensile strength</b> (EN ISO 527)	Along: min. 16 N/mm <sup>2</sup> Across: min. 16 N/mm <sup>2</sup>
<b>Elongation at break</b> (EN ISO 527)	Along: min. 250% Across: min. 250%
<b>Shelf life</b> <sup>(2)</sup>	2 years
<b>Application temperature</b>	10° C – 25° C
<b>Proposed application technique</b>	Wet application
<b>Maximum service life</b> Applies for vertical outdoor exposure	5 years

