

Release Liner

Matt PET, siliconized on one side, 75 µm

Adhesive

Solvent polyacrylate, transparent, permanent

Technical Data

Total Thickness	250 micron
Dimensional stability ⁽¹⁾ (FINAT TM 14)	Adhered to steel, shrinkage 0,2 mm max.
Resistance to solvents and chemicals Immerse for 1 hour at RT (water), 30 Min at 45°C (acid, Pancreatin, tree gum), 10 Min (Gasoline E10), Check after 24 hours at RT	Water Sulfuric Acid (10%) Hydrochloric Acid (10%) Bird droppings (Pancreatin) No Detrimental Effect Tree gum Gasoline E10
Gloss	>90 (GU)
Adhesive Power ^l (180°, after 24h stainless steel)	≥ 20 N/25 mm
Tensile strength (EN ISO 527)	Along: min. 20 N/mm ² Across: min. 20 N/mm ²
Elongation at break (EN ISO 527)	Along: min. 300% Across: min. 300%
Shelf life ⁽²⁾	2 years
Application temperature	10° C – 25° C
Proposed application technique	Wet application
Maximum service life Applies for vertical outdoor exposure	7 years

